


DIAMOND QUALITY QUICK REFERENCE GUIDE

DIAMOND SHAPES



CARAT WEIGHT SIZES

| | | | | | | | | |
|--------------|--------|--------|--------|--------|--------|--------|--------|--------|
| Carat Weight | 3.00 | 2.50 | 2.00 | 1.50 | 1.00 | 0.75 | 0.50 | 0.25 |
| Approx. Size | | | | | | | | |
| Diameter | 9.20mm | 8.60mm | 8.00mm | 7.30mm | 6.40mm | 5.80mm | 5.10mm | 4.10mm |


COLOR



CLARITY

| | | | | | | | | | | |
|--------------------------|-----------------------------|------------------------|------------------------|-------------------|-------------------|------------------|----|----|----|----|
| FL | IF | VVS1 | VVS2 | VS1 | VS2 | S1 | S2 | I1 | I2 | I3 |
| FLAWLESS - INTERNALLY FL | VERY VERY SLIGHTLY INCLUDED | VERY SLIGHTLY INCLUDED | VERY SLIGHTLY INCLUDED | SLIGHTLY INCLUDED | SLIGHTLY INCLUDED | INCLUDED / PIQUE | | | | |

CUT



| | Traditional IDEAL-(30) | Excellent-(30) | Very Good-(25) |
|------------------|------------------------|------------------|--------------------------|
| Table Size | 53 - 57% | 52 - 62% | 50-51% or 62-66% |
| Depth % | 59.8 - 62.4% | 57.5 - 63.0% | 56.0-57.4% or 63.1-64.5% |
| Crown Angle | 33.7 - 35.8° | 31.5 - 36.5° | 26.5-31.4° or 36.6-38.5° |
| Pavilion Angle | 40.1 - 41.2° | 40.1 - 41.8° | 39.8-40.0° or 41.9-42.4° |
| Girdle Thickness | Thin - Sl. Thick | Thin - Sl. Thick | Very Thin or Thick |
| Culet | None - Small | None - Small | Medium |



GEM CERTIFICATION & ASSURANCE LAB
ISO 17025 ACCREDITED FORENSIC LABORATORY